

IN THE SPECIFICATION

Please replace paragraph [0028] with the following new paragraph:

--The total weight of all filler relative in the weight of the TIM can be in the range of approximately 10 – 95% weight filler. The total weight of fusible filler can be in the range of approximately 60 – 90% by weight of the total weight of the TIM. The total weight of non-fusible filler can be in the range of approximately 5 – 49% by weight of the total weight of the TIM. With regards to the filler only, the volume percent of fusible filler to non-fusible filler can be in a range of approximately 5 – 95 volume % fusible filler. The preferred range can be approximately 10 – 50 volume % fusible filler. A mean particle diameter for the non-fusible particle can be approximately 25 microns.--